

# DensiCrete

## Product Bulletin

### Clarification of Independent Test Procedures

In several of the independent laboratory tests performed by Pittsburgh Testing Laboratories, the application procedure calls for a “single saturation coat” of **DensiCrete** to be applied to the concrete test object.

The term “single saturation coat” means that the **DensiCrete** has been applied in successive coats, each coat having a spread rate of approximately 150 square feet per coat, until the product puddles on the surface, indicating that any additional coats would not be absorbed into the object.

The company cannot determine the number of coats required to achieve saturation. Saturation is dependent upon the concrete’s density, surface porosity, temperature, trowel finish, and other factors. Therefore, to determine what constitutes a saturation coat, the end user should apply successive coats until the **DensiCrete** will no longer absorb into the concrete and continues to puddle for a seven minute period.